

TECHNICAL SHEET

SKYBIT G200



Waterproofing membrane with a glass fabric carrier

Product description: SKYBIT G200 is a waterproofing membrane made from a glass fabric reinforcement, that is coated on both sides with plastomer modified bitumen. The membrane is on the upper side protected by sand and on the bottom side by polimeric sheeting.

Characteristics of the product: SKYBIT G200 meets the demands of the standards EN 13707, EN 13969 Type T. Glass fabric gives the product good mechanical characteristics and dimensional stability.

Characteristics	EN Method	Unit	Declaration EN 13707:2004+A2:2009 EN13969:2004 a EN 13969:2004/A1:2006
Reinforcement	glass fabric		
Surface protection	sand / polymeric sheeting		
Length	1848-1	m	≥ 8,0
Width	1848-1	m	≥ 1,0
Straightness	1848-1	20mm/10m	pass
Thickness	1849-1	mm	≥ 4,0
Watertightness	1928/2000	kPa	≥ 60
Durability of water tightness against artificial ageing by long term exposure to elevated temperature (12 weeks at 70°C)	1296/1928	kPa	≥ 60
Flexibility at low temperature	1109	°C	≤ 0
Flow resistance at elevated temperature	1110	°C	≥ 100
Resistance to tearing	12310-01	N	≥ 200
- longitudinal			
- transversal			≥ 200
Shear resistance to joints	12317-1	N	≥1000
- longitudinal			
- transversal			≥1000
Dimensional stability	1107-1	%	NPD
- longitudinal			
- transversal			NPD
Water vapor transmission properties, Sd	1931	μ	NPD
External fire performance	13501-5	class	Froof (t1)
Reaction to fire	13501-1	class	E
Chemical resistance	1847/13969 Príloha A	-	pass
Resistance to static loading	12730/A	kg	≥ 5
Resistance to static loading	12730/B	kg	≥ 10
Resistance to impact	12691/A	mm	≥ 900
Resistance to impact	12691/B	mm	≥ 1000
Tensile strength	12311-1	N/50mm	≥1000
- longitudinal			
- transversal			≥1000
Elongation	12311-1	%	≥ 2,0
- longitudinal			
- transversal			≥ 2,0
Content of hazardous substances	Annex ZA	/	does not contain

Instruction for use and installation:

SKYBIT G200, is used regarding the demands of the standards as an intermediate layer in two or more layered flat roof systems which are protected by UV-resistant membrane. It is used for less demanding underground waterproofing systems, i.e, the resistance to ponding water and in two-layer systems of vertical and horizontal waterproofing that are exposed to water pressure. The membrane is installed by torch with 10cm overlaps, which must be waterproof.

Storage and transport:

The rolls have to be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

The carrier is responsible for the correct transport.

Disposal considerations of waste:

For the removal of waste of product it is necessary to follow the valid local environmental regulations.



The product is in conformity with with **EN 13707:2004+A2:2009** and **EN 13969:2004** and **EN 13969:2004/A1:2006** Type T.

Number EC certificate of control of quality: **1404 – CPR – 2323**

The system of quality is conform with **EN ISO 9001**.